



F - 350

ANÁLISIS QUÍMICO

	<u>%</u>
SiO ₂	49,00 +/- 1,0
Al ₂ O ₃	36,50 +/- 1,0
Fe ₂ O ₃	0,45 +/- 0,15
TiO ₂	0,15 +/- 0,05
CaO	0,10 +/- 0,05
K ₂ O	0,60 +/- 0,30
P.C	12,80 +/- 0,50
CADMIO:	< 2 ppm
PLOMO:	< 30 ppm
DIOXINAS:	Máx. 500pg EQT-PCDD/F-OMS/kg

**ANÁLISIS GRANULOMÉTRICO
TECNICA LASER**

	<u>%</u>
< 10 micras	70,5 +/- 5
< 2 micras	14,0 +/- 5

ANÁLISIS MINERALÓGICO

CAOLINITA	86 +/- 2,0
ILLITA/MOCOVITA	7 +/- 2,0
CUARZO	6 +/- 2,0

COLORIMETRIA

L	94,9 +/- 2,0
a	0,25 +/- 0,5
b	3,80 +/- 2,0

Oficinas y planta:

Carretera N-II; Km.- 60
19193 Taracena (Guadalajara) España
Tel. 949227165
Fax 949216903

Minas:

19463 Poveda de la Sierra
Guadalajara (España)

